

Glaze recipes: cone 10

for Boxmoor Kiln wood-firings

Glazes

Ash glaze;

David Frith

Ash glaze 33.3

Potash Feldspar 33.3

Flint 33.3

Sycamore Ash -Blue

Southern Ceramic glaze group

Flint 33

Nepheline Syenite 33

Wood Ash 33

Mick Casson

Ash 50

Ball clay 25

China clay 25

Shino;

ATBall clay 50

Potash feldspar 50

Ruthane Tudball

Red Shino

ATBall 1 part

Nepheline syenite 1 part

Soda Feldspar 1 part

Svend Bayer

Shino

Ball clay 20

Potash Feldspar 40

Nepheline syenite 40

Celadon;

Potash Feldspar 20
Nepheline syenite 20
ATBall clay 20
Whiting 20
Talc 10
Quartz 10
Iron Oxide 1.5
(Bone ash) 1

Copper Red;

Blue;

Tenmoku;

Slips

Flash Slip

Fireclay as slip - toasty surface

Porcelain slip (Casting) + 10% quartzite

Batt Wash

Alumina hydrate 50 (3parts)
China clay 50 (1part)

Wadding

Alumina hydrate 5parts
China clay 1part
Bentonite 3%